

Company with Quality System in accordance with ISO 9001: 2015 **Certified by Bureau Veritas** 

## Technical data sheet

Total thickness (carrier + adhesive): 0.21 mm

# **BS 26.02**

Main carrier:	TRANSPARENT PET FILM
Secondary carrier:	
Main liner:	HAVANA SILICONIZED GLASSINE PAPER
Secondary liner:	
Open side adhesive:	MODIFIED ACRYLIC
Closed side adhesive:	MODIFIED ACRYLIC

#### Adhesive properties

Peel 90° on steel		Open side	17	M.U.	Method
		Closed side	17	N/25 mm	BS 35 - AFERA 5001
Rolling ball test		Open side	7	M.U.	Method
		Closed side	7	Cm	BS 12 - PSTC-6
Quick stick on steel		Open side	26	M.U.	Method
		Closed side	26	N/25 mm	BS 6 - AFERA 4015
Shear on steel	KG	Open side	100	M.U.	Method
		Closed side	100	Hours	BS 68 - AFERA 5012

### **Temperature resistance**

Long term	120	M.U.: °C
Short term	200	M.U.: °C

#### **Mechanical properties**

Tensile strength at break Longitudinal		Min.	Max. 3000	M.U. Kg/cm2	Method ASTM D 882
Tensile strength at break Transversal		Min. 2000	Max. 3000	M.U. Kg/cm2	Method ASTM D 882
Elongation at break Longitudinal	Z	Min.	Max.	M.U.: %	Method ASTM D 882
Elongation at break Transversal	No.	Min.	Max.	M.U.: %	Method ASTM D 882



# Technical data sheet

Company with Quality System in accordance with ISO 9001: 2015 Certified by Bureau Veritas

Total thickness (carrier + adhesive): 0.21 mm

# **BS 26.02**

#### **Description**

The product is made up of a transparent polyester film carrier and a havana siliconized glassine paper

The acrylic adhesives system (wet-style) provides high adhesion performances on both sides.

### **Applications**

Ideal for fixing cable ducts and LED strips.

Suitable for lamination of various types of material used in furniture production.

Ideal for fixing of trims and decorative elements, fixing gaskets and sealing profiles, mosquito net and roller-blind assembling and for insulation of roof and walls in building industry.

Recommended for fixing on uneven surfaces, in leather, leatherette or fabric on fashion wear and and accessories in the clothing, footwear and leather goods sectors.

Suitable for strutural bonding of car components in the automotive industry.

#### **Product PLUS**

Very high adhesion and cohesion.

Perfect bond to low surface energy materials.

Very high resistance to high temperature and atmospheric agents.

## Recommendations for correct use

For a proper storage of the product we recommend to keep the product in the original package until it is needed and use it within 12 months from delivery.

The storage shall be carried out at a room temperature between 15°C and 25°C, and a relative humidity < 65%.

Once removed from the packaging, place the product vertically and protect it from dust. Do not expose product and packaging to direct sunlight and heat sources.

**Surface cleaning**The product shall be applied on sufficiently flat surfaces and with no non-stick coating.

In order to obtain a correct product adhesion level on surfaces, it is indispensable that the surfaces are properly cleaned before the application. It is recommended to use quick-evaporating solvents.

After cleaning make sure that the solvent has completely evaporated, by waiting for a sufficiently long period of time or by drying the surface with a completely dry cloth.

#### Application

As adhesive tape is pressure-sensitive, it is necessary a proper pressing pressure on the back of the tape, once applied on the surface, to ensure the grip of the adhesive and a full lamination.

#### Measuring tolerances

The tape cutting width tolerance can vary within a range of ±2.0 mm. Different tolerances for specific formats and measures can be available on request.

#### Disposal

It is recommend to dispose the product after use according to the specific regulations of the country it was used in.

For additional information, please refer to our Technical Office: info.tapes@biesSseworld.com +39 02 90 11 11 18