

Company with Quality System in accordance with ISO 9001: 2015 Certified by Bureau Veritas

Technical data sheet

Total thickness (carrier + adhesive): 0.41 mm

BS MOUNT 15.150 TT

Main carrier:	PINK PE FOAM			
Secondary carrier:	TRANSPARENT REINFORCEMENT FILM			
Main liner:	TRANSPARENT SILICONE ORANGE PEEL EMBOSSED PP FILM			
Secondary liner:	-			
Open side adhesive:	NATURAL RUBBER			
Closed side adhesive:	NATURAL RUBBER			

Adhesive properties

Peel 90° on steel		Open side	6	M.U.	Method
		Closed side	7	N/25 mm	BS 35 - AFERA 5001
Rolling ball test		Open side	1	M.U.	Method
lesi		Closed side	1	Cm	BS 12 - PSTC-6
Quick stick on steel	î zî	Open side	8	M.U.	Method
		Closed side	10	N/25 mm	BS 6 - AFERA 4015
Shear		Open side	60	M.U.	Method
on steel	КС	Closed side	60	Hours	BS 254

Temperature resistance

Long term	+5°/+60°	M.U.: °C
Short term	+5°/+80°	M.U.: °C

Mechanical properties

Tensile strength at break Longitudinal	Min.	Max.	M.U. kPa	Method ISO-1926
Tensile strength at break	Min.	Max.	M.U.	Method
Transversal	14267	14267	kPa	ISO-1926
Elongation	Min.	Max.		Method
at break Longitudinal	56	56	M.U.: %	ISO-1926
Elongation	Min.	Max.		Method
at break Transversal	57	57	M.U.: %	ISO-1926

Note: All above information are believed to be true and reliable but they are given only for guidance. They do not constitute a warranty or a specification. The characteristics refer to average values, relevant to samples collected from our production. Users must confirm the suitability of the products through their own tests. BiesSse Tape reserve the right to introduce at any moment and without warning those changes that they deem necessary. Tolerance of Technical Data: \pm 30%



Company with Quality System in accordance with ISO 9001: 2015 Certified by Bureau Veritas

Technical data sheet

Total thickness (carrier + adhesive): 0.41 mm

BS MOUNT 15.150

Description

The product is made up of a laminated multi-layer, calibrated thickness, closed cell polyethylene, physically reticulated, foam carrier and a transparent orange peel embossed polypropylene silicone film liner. On one side, the PE foam carrier is reinforced with a transparent film.

The natural rubber adhesive system (wet-style), on both sides, provides very high adhesion performances.

Medium-high compressibility, identified through the pink coloured foam.

Applications

Ideal for Narrow Web printing of labels.

Suitable for combination print with prevailing screens, shades, lines and fine types.

Recommended for medium and high thickness photopolymer plates.

Ideal for mounting operations on steel and aluminium cylinders.

Optimal printing results at very high speed and long printing runs.

Product PLUS

The surface structure of the liner is especially designed to impress undulations in the adhesive for the potential exit of air bubbles trapped between the double-sided adhesive tape and the cylinder or the plate during mounting operations.

High resilience foam

High adhesion level, ideal for maximum hold on either plates or cylinders, especially in edge to edge plate mounting operations.

Recommendations for correct use

Storage

For a proper storage of the product we recommend to keep the product in the original package until it is needed and use it within 12 months from delivery.

The storage shall be carried out at a room temperature between 15°C and 25° C, and a relative humidity < 65%.

Once removed from the packaging, place the product vertically and protect it from dust. Do not expose product and packaging to direct sunlight and heat sources.

Surface cleaning The product shall be applied on sufficiently flat surfaces and with no non-stick coating.

In order to obtain a correct product adhesion level on surfaces, it is indispensable that the surfaces are properly cleaned before the application. It is recommended to use quick-evaporating solvents.

After cleaning make sure that the solvent has completely evaporated, by waiting for a sufficiently long period of time or by drying the surface with a completely dry cloth.

Application

As adhesive tape is pressure-sensitive, it is necessary a proper pressing pressure on the back of the tape, once applied on the surface, to ensure the grip of the adhesive and a full lamination.

Measuring tolerances

The tape cutting width tolerance can vary within a range of ±2.0 mm. Different tolerances for specific formats and measures can be available on request.

Disposal

It is recommend to dispose the product after use according to the specific regulations of the country it was used in.

For additional information, please refer to our Technical Office: info.tapes@biesSseworld.com +39 02 90 11 11 18

Note: All above information are believed to be true and reliable but they are given only for guidance. They do not constitute a warranty or a specification. The characteristics refer to average values, relevant to samples collected from our production. Users must confirm the suitability of the product through their own tests. BiesSse Tape reserve the right to introduce at any moment and without warning those changes that they deem necessary. Tolerance of Technical Data: ± 30%